

Appl. No.: 10/817,366

Art Unit: 1712 Docket No.: B03-30

Reply to Office Action of August 3, 2005

### LISTING OF CLAIMS

1. (Currently amended) A golf ball comprising:  
a core having a first outer surface;  
a cover; and  
an intermediate layer disposed between the core and the cover, the intermediate layer comprising a high melt flow non-ionic hydrophobic stiff fluoropolymer comprising a copolymer of tetrafluoroethylene and hexafluoropropylene having a melt viscosity of 10 KPoise or less at 230°C, a surface energy of less than about 75 dyne/cm<sup>2</sup> and having a second outer surface;  
wherein at least one of the first or second outer surfaces are treated with a functional silane such that a sufficient number of surface amine, hydroxyl, carboxylic acid, or epoxy groups are available for binding to an adjacent layer; and wherein the intermediate layer has a specific gravity of 1.3 to about 1.6 in the absence of a density-adjusting filler.
2. (Original) The golf ball of claim 1, wherein the functional silane is an aminosilane that forms surface amine groups for binding.
3. (Original) The golf ball of claim 1, wherein the non-ionic hydrophobic stiff fluoropolymer has a surface energy of less than about 50 dyne/cm<sup>2</sup>.
4. (Original) The golf ball of claim 1, wherein the non-ionic hydrophobic stiff fluoropolymer has a surface energy of less than about 40 dyne/cm<sup>2</sup>.
5. (Original) The golf ball of claim 1, wherein the non-ionic hydrophobic stiff fluoropolymer is a homopolymer, copolymer, or terpolymer formed from a polymerization of one or more non-ionic fluoromonomers.
6. (Original) The golf ball of claim 1, wherein the intermediate layer further comprises a thermoplastic material comprising polyesterester block copolymers, polyetherester block copolymers, polyetheramide block copolymers, partially or fully neutralized ionomer resins, dynamically vulcanized thermoplastic elastomers, hydrogenated styrene-butadiene elastomers with functional groups attached, thermoplastic polyurethanes, thermoplastic polyesters,

Appl. No.: 10/817,366

Art Unit: 1712 Docket No.: B03-30

Reply to Office Action of August 3, 2005

metallocene polymers; styrene-propylene-diene rubbers; polybutadienes; chloroprene rubbers; acrylonitrile rubbers; acrylonitrile-butadiene rubbers; ethylene/propylene/diene terpolymers; polypropylene resins; epoxy; polyurea; styrene-ethylene block copolymers; maleic anhydride or succinate modified metallocene catalyzed ethylene copolymers; chlorinated polyethylenes; polysulfide rubbers; fluorocarbons; or polymethylmethacrylate.

7. (Original) The golf ball of claim 1, wherein the adjacent layer is the core or the cover.
8. (Original) The golf ball of claim 1, wherein the non-ionic fluoropolymer has a material hardness between about 25 and about 75 Shore D.
9. (Currently amended) The golf ball of claim [[7]] 8, wherein the non-ionic fluoropolymer of the intermediate layer has a material hardness of between about 50 and about 70 Shore D.
10. (Original) The golf ball of claim 1, wherein the intermediate or cover layer has a thickness between about 0.005 inches and about 0.085 inches.
11. (Currently amended) The golf ball of claim [[9]] 10, wherein the intermediate or cover layer has a thickness between about 0.030 inches and about 0.060 inches.
12. (Original) The golf ball of claim 1, wherein the golf ball has an outer diameter between about 1.500 inches and about 1.650 inches.
13. (Original) The golf ball of claim 1, wherein the golf ball has an outer diameter between about 1.550 inches and about 1.640 inches.
14. (Canceled)
15. (Canceled)

Appl. No.: 10/817,366

Art Unit: 1712 Docket No.: B03-30

Reply to Office Action of August 3, 2005

16. (Original) The golf ball of claim 1, wherein the core comprises a center and at least one outer core layer.
17. (Original) The golf ball of claim 14, wherein the center is solid, hollow, liquid-filled, gel-filled, or gas-filled.
18. (Original) The golf ball of claim 14, wherein the aminosilane comprises  $\gamma$ -aminopropyltriethoxysilane;  $\gamma$ -aminopropyltriethoxysilane;  $\gamma$ -aminopropyltriethoxysilane; aminoalkyl silicone solution; modified aminoorganosilane;  $\gamma$ -aminopropyltrimethoxysilane; n- $\beta$ -(aminoethyl)- $\gamma$ -aminopropyltrimethoxysilane; modified aminoorganosilane (40% in methanol); modified aminosilane (50% in methanol); triaminofunctional silane; bis-( $\gamma$ -trimethoxysilylpropyl)amine; n-phenyl- $\gamma$ -aminopropyltrimethoxysilane; organomodified polydimethylsiloxane; polyazamide silane (50% in methanol); or n- $\beta$ -(aminoethyl)- $\gamma$ -aminopropylmethyldimethoxysilane.
19. (Original) The golf ball of claim ~~[[17]]~~ 18, wherein the aminosilane is n- $\beta$ -(aminoethyl)- $\gamma$ -aminopropyltrimethoxysilane.
20. (Original) The golf ball of claim 1, wherein the cover comprises a castable or non-castable thermoplastic or thermosetting material comprising partially- or fully-neutralized ionomer resins; epoxy; polyurethanes comprising polyols and polyisocyanates; balata; vinyl resins; polyolefins; polyureas; polyamides; acrylic resins and blends thereof; block copolymers; copoly(ether-amide); polyphenylene oxide resins and blends thereof; thermoplastic polyesters; blends and alloys including polycarbonate with acrylonitrile butadiene styrene and polyvinyl chloride with acrylonitrile butadiene styrene; blends of thermoplastic rubbers with polyethylene and propylene; or a mixture thereof.
21. (Original) The golf ball of claim 1, wherein the core has a Shore D hardness of less than about 60.

Appl. No.: 10/817,366

Art Unit: 1712 Docket No.: B03-30

Reply to Office Action of August 3, 2005

22. (Original) The golf ball of claim 1, wherein the cover comprises at least one additive comprising antioxidants; catalysts; colorants including pigments and dyes; hindered amine light stabilizers; optical brighteners; UV absorbers; fillers; metals; plasticizers; surfactants; viscosity modifiers; compatibility agents; dispersing agents; foaming agents; reinforcement agents; release agents; or a mixture thereof.
23. (Original) The golf ball of claim 1, where the non-ionic hydrophobic stiff fluoropolymer has a water absorption at 20°C immersion for 24 hr of no greater than about 0.07%.
24. (Currently amended) A golf ball comprising:  
a core having a first outer surface;  
a cover; and  
an intermediate layer disposed between the core and the cover, the intermediate layer comprising a high melt flow non-ionic hydrophobic stiff fluoropolymer comprising a copolymer of tetrafluoroethylene and hexafluoropropylene having a melt viscosity of 10 KPoise or less at 230°C, a surface energy of less than about 55 dyne/cm<sup>2</sup>, a water absorption at 20°C immersion for 24 hr of less than about 0.1%, and having a second outer surface;  
wherein at least one of the first or second outer surfaces are treated with an aminosilane such that a sufficient number of surface amine groups are present and result in the treated layer having a peel strength of at least about 5 lb/in; and wherein the intermediate layer has a specific gravity of 1.3 to about 1.6 in the absence of a density-adjusting filler.
25. (Currently amended) The golf ball of claim ~~[[23]]~~ 24, wherein the peel strength is at least about 10 lb/in.
26. (Currently amended) The golf ball of claim ~~[[22]]~~ 25, wherein the peel strength is at least about 15 lb/in.
27. (Currently amended) The golf ball of claim ~~[[23]]~~ 24, wherein the aminosilane comprises  $\gamma$ -aminopropyltriethoxysilane;  $\gamma$ -aminopropyltriethoxysilane;  $\gamma$ -aminopropyltriethoxysilane; aminoalkyl silicone solution; modified aminoorganosilane;  $\gamma$ -aminopropyltrimethoxysilane; n-

Appl. No.: 10/817,366

Art Unit: 1712 Docket No.: B03-30

Reply to Office Action of August 3, 2005

$\beta$ -(aminoethyl)- $\gamma$ -aminopropyltrimethoxysilane; modified aminoorganosilane (40% in methanol); modified aminosilane (50% in methanol); triaminofunctional silane; bis-( $\gamma$ -trimethoxysilylpropyl)amine; n-phenyl- $\gamma$ -aminopropyltrimethoxysilane; organommodified polydimethylsiloxane; polyazamide silane (50% in methanol); or n- $\beta$ -(aminoethyl)- $\gamma$ -aminopropylmethyldimethoxysilane.

28. (Currently amended) A golf ball comprising:

a core having a first outer surface;

a cover; and

an intermediate layer disposed between the core and the cover, the intermediate layer comprising a high melt flow non-ionic hydrophobic stiff fluoropolymer comprising a copolymer of tetrafluoroethylene and hexafluoropropylene having a melt viscosity of 10 KPoise or less at 230°C, a surface energy of no greater than about 55 dyne/cm<sup>2</sup>, a coefficient of friction of less than about 0.55, and having a second outer surface;

wherein at least one of the first or second outer surfaces are treated with n- $\beta$ -(aminoethyl)- $\gamma$ -aminopropyltrimethoxysilane in an amount sufficient to result in a peel strength between treated layers of at least about 10 lb/in; and wherein the intermediate layer has a specific gravity of 1.3 to about 1.6 in the absence of a density-adjusting filler.

29. (Currently amended) The golf ball of claim [[25]] 28, wherein the coefficient of friction of less than about 0.45.